

# UTILITY PATENT APPLICATION TRANSMITTAL (Large Entity)

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Docket No.  
EN997064

Total Pages in this Submission  
3

## TO THE ASSISTANT COMMISSIONER FOR PATENTS

Box Patent Application  
Washington, D.C. 20231

Transmitted herewith for filing under 35 U.S.C. 111(a) and 37 C.F.R. 1.53(b) is a new utility patent application for an invention entitled:

**COPPER CLEANING COMPOSITIONS, PROCESSES AND PRODUCTS DERIVED THEREFROM**

and invented by:

Kathleen L. Covert (deceased) by Kelly Hawley executrix  
John M. Lauffer  
Peter A. Moschak

If a **CONTINUATION APPLICATION**, check appropriate box and supply the requisite information:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: \_\_\_\_\_

Which is a:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: \_\_\_\_\_

Which is a:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No.: \_\_\_\_\_

Enclosed are:

### Application Elements

1. ☒ Filing fee as calculated and transmitted as described below
2. ☒ Specification having 35 pages and including the following:
  - a. ☒ Descriptive Title of the Invention
  - b. ☐ Cross References to Related Applications (if applicable)
  - c. ☐ Statement Regarding Federally-sponsored Research/Development (if applicable)
  - d. ☐ Reference to Microfiche Appendix (if applicable)
  - e. ☒ Background of the Invention
  - f. ☒ Brief Summary of the Invention
  - g. ☐ Brief Description of the Drawings (if drawings filed)
  - h. ☒ Detailed Description
  - i. ☒ Claim(s) as Classified Below
  - j. ☒ Abstract of the Disclosure

# UTILITY PATENT APPLICATION TRANSMITTAL (Large Entity)

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Docket No.  
EN997064

Total Pages in this Submission  
3

## Application Elements (Continued)

3. ☐ Drawing(s) (when necessary as prescribed by 35 USC 113)
- a. ☐ Formal Number of Sheets \_\_\_\_\_
- b. ☐ Informal Number of Sheets \_\_\_\_\_
4. ☒ Oath or Declaration
- a. ☐ Newly executed (original or copy) ☒ Unexecuted
- b. ☐ Copy from a prior application (37 CFR 1.63(d)) (for continuation/divisional application only)
- c. ☒ With Power of Attorney ☐ Without Power of Attorney
- d. ☐ DELETION OF INVENTOR(S)  
Signed statement attached deleting inventor(s) named in the prior application,  
see 37 C.F.R. 1.63(d)(2) and 1.33(b).
5. ☐ Incorporation By Reference (usable if Box 4b is checked)  
The entire disclosure of the prior application, from which a copy of the oath or declaration is supplied under Box 4b, is considered as being part of the disclosure of the accompanying application and is hereby incorporated by reference therein.
6. ☐ Computer Program in Microfiche (Appendix)
7. ☐ Nucleotide and/or Amino Acid Sequence Submission (if applicable, all must be included)
- a. ☐ Paper Copy
- b. ☐ Computer Readable Copy (identical to computer copy)
- c. ☐ Statement Verifying Identical Paper and Computer Readable Copy

## Accompanying Application Parts

8. ☒ Assignment Papers (cover sheet & document(s))
9. ☐ 37 CFR 3.73(B) Statement (when there is an assignee)
10. ☐ English Translation Document (if applicable)
11. ☒ Information Disclosure Statement/PTO-1449 ☒ Copies of IDS Citations
12. ☐ Preliminary Amendment
13. ☒ Acknowledgment postcard
14. ☒ Certificate of Mailing
- ☐ First Class ☒ Express Mail (Specify Label No.): EM589154083US

# UTILITY PATENT APPLICATION TRANSMITTAL (Large Entity)

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Docket No.  
EN997064

Total Pages in this Submission  
3

## Accompanying Application Parts (Continued)

15. ☐ Certified Copy of Priority Document(s) (if foreign priority is claimed)
16. ☒ Additional Enclosures (please identify below):


Copy of Letters Testamentary, Letter to Assistant Commissioner

## Fee Calculation and Transmittal

### CLAIMS AS FILED

For	#Filed	#Allowed	#Extra	Rate	Fee
Total Claims	20	- 20 =	0	x \$18.00	\$0.00
Indep. Claims	4	- 3 =	1	x \$78.00	\$78.00
Multiple Dependent Claims (check if applicable) <input type="checkbox"/>					\$0.00
BASIC FEE					\$760.00
OTHER FEE (specify purpose)					\$0.00
TOTAL FILING FEE					\$838.00

- ☐ A check in the amount of \_\_\_\_\_ to cover the filing fee is enclosed.
- ☒ The Commissioner is hereby authorized to charge and credit Deposit Account No. **09-0457** as described below. A duplicate copy of this sheet is enclosed.
- ☒ Charge the amount of **\$838.00** as filing fee.
  - ☒ Credit any overpayment.
  - ☒ Charge any additional filing fees required under 37 C.F.R. 1.16 and 1.17.
  - ☐ Charge the issue fee set in 37 C.F.R. 1.18 at the mailing of the Notice of Allowance, pursuant to 37 C.F.R. 1.311(b).

  
Signature

Lawrence R. Fraley/Reg. # 26,885  
IBM Corporation/Dept. N50/40-4  
1701 North Street  
Endicott, NY 13760

Dated: March 22, 1999

CC:

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Patent Application:	:	Group Art Unit: N/A
Covert et al.	:	Examiner: N/A
Serial No.:	:	Docket No.: EN997064
Filed: Herewith	:	IBM Corporation
Title: Copper Cleaning	:	Intellectual Property Law
Compositions, Processes	:	1701 North Street
And Products Derived Therefrom	:	Endicott, NY 13760

Assistant Commissioner For Patents  
Washington, DC 20231

COMMUNICATION


Dear Sir:

We are enclosing a true copy of the "Certificate of Appointment (Estate)" for the Estate of Kathleen L. Covert, deceased, an inventor on the above identified application. These Letters Testamentary certify that Kelly Hawley is qualified according to law as Independent Administrator of the Estate of Kathleen L. Covert.

The Commissioner is authorized to charge any fees associated with this submission to Deposit Account number 09-0457.

Respectfully Submitted,

Date: Mar. 22, 1999

  
Lawrence R. Fraley  
Reg. No. 26,885  
Phone: (607) 755-3207  
Fax: (607) 755-3250

EN997064

STATE OF NEW YORK  
COUNTY OF BROOME }  
SURROGATE'S COURT } ss:

**CERTIFICATE  
OF  
APPOINTMENT  
(Estate)**

IT IS HEREBY CERTIFIED that letters in the estate of the decedent named below have been granted by this Court. The named representative(s) is authorized and empowered to do and perform all acts requisite to the proper administration and disposition of the estate of such decedent, in accordance with the laws of this State and the limitations, if any, contained in said letters as indicated below.

Name of Decedent: KATHLEEN L. COVERT 98-0329  
Domicile of Decedent  
Date/Place of Death: TOWN OF DICKINSON  
04-03-1998 MIDDLETOWN TWP. PA  
Representative(s)  
to Whom  
Letters Issued:  
Type of Letters Issued: LETTERS TESTAMENTARY  
Date Letters Issued: MAY 21, 1998

and such letters are unrevoked and in force as of this date.

(L.S.)

IN TESTIMONY WHEREOF, the seal of the  
Surrogate's Court of Broome County, New  
York, has been affixed.

WITNESS, HON. JOHN M. THOMAS,  
Surrogate of said County at the City of  
Binghamton, New York

THIS CERTIFICATE IS NOT VALID  
WITHOUT A RAISED SEAL OF THE COURT

Date: SEPTEMBER 15, 1998

*Marilyn A. Vesco*  
Chief Clerk of the Surrogate's Court

**APPLICATION**

**FOR**

**UNITED STATES LETTERS PATENT**

APPLICANT(S) NAME: K. L. Covert (deceased)  
J. M. Lauffer  
P. A. Moschak

TITLE: COPPER CLEANING COMPOSITIONS, PROCESSES AND PRODUCTS  
DERIVED THEREFROM

DOCKET NO. EN997064

**INTERNATIONAL BUSINESS MACHINES CORPORATION**

**Certificate of Mailing Under 37 CFR 1.10**

I hereby certify that, on the date shown below, this correspondence is being deposited with the United States Postal Service in an envelope addressed to the Assistant Commissioner for Patents, Washington, D.C., 20231 as "Express Mail Post Office to Addressee".

"Express Mail" Label Number EM589154083US

On 03/23/99

Bethany J. Fitzpatrick

*Typed or Printed Name of Person Mailing Correspondence*

Bethany J. Fitzpatrick  
*Signature of Person Mailing Correspondence*

3/23/99  
*Date*

COPPER CLEANING COMPOSITIONS, PROCESSES  
AND PRODUCTS DERIVED THEREFROM

Field of the Invention:

5 This invention pertains generally to compositions and processes for cleaning copper or copper alloy (hereinafter collectively referred to as copper) surfaces during the fabrication of microelectronic packages and, more particularly, to selective copper microetching at the interface or in the vicinity of noble metals and their alloys typically found at plated edge connectors, contact pads, plated through holes (PTH), and embedded resistors.

10 As is known in the art, there is a trend to reduce the size of microelectronic packages. This results in "dense" microelectronic packages having finer and thinner printed circuit lines, smaller diameter plated through holes, and more multilayering. One problem with making dense printed circuit boards is that the yield from the manufacture of these boards is relatively low due to such problems as poor adhesion of layers in  
15 packages, shorting or bridging caused by contaminants, and open circuits due to breaking of the microcircuit lines typically caused by harsh cleaning or galvanic etching. It has therefore become a more difficult problem since cleaning of the microelectronic packages must be performed during their manufacture, yet precise conditions must be maintained otherwise the fragile microcircuits will be irrevocably damaged during such cleaning  
20 processes.

## BACKGROUND OF THE INVENTION

At the present time, cleaning of copper on microelectronic substrates is performed either by chemical means, mechanical means or a combination of both. Contaminants present during printed wiring board (PWB) manufacture include photoresist materials, residual organic and residual metallic contaminants such as alkali metals and native/metallic oxides. Metallic films comprising metal oxides and metal halides are also inadvertently deposited onto electronic packages during immersion into etchant or resist stripper baths. If mechanical means have been used for cleaning, there is the possibility that residues of abrasive particles, such as pumice, will be adsorbed on the surface of the copper.

This cleaning process also called "microetching or soft etching" is ideally designed to exclusively clean the surface of the copper without diminishing or changing the dimensions of the copper itself or attacking adjacent materials (i.e., there is complete selectivity for eliminating surface contaminants on the copper and no bulk erosion or attack of the electrical microcomponents). The benefit of such idealized cleaning is to provide microelectronic packages with reduced rates of malfunction or failure due to delamination, shorting or open circuits.

For example, it is known that corrosive chlorides can be deposited on microelectronic packages causing weakening or embrittlement of electrical connectors as well as delaminate the layers of the package resulting in current leakages or physical failure. As miniaturization of microelectronic packaging is an important target, the problem of obtaining high levels of selectivity has been exacerbated due to the fragility of microcomponents such as fine-line copper circuits. Compounding the problem of finding an ideal microetching process is the desire to provide a manufacturing process that is fast



and efficient. However, typically the faster the cleaning process the lower the selectivity which can ultimately be achieved. This is well known in the art of copper polishing where it is preferred that mild chemical polishing agents are used at longer processing times in order to minimize the loss of bulk copper. It is also recognized that although  
5 numerous chemical copper-etchant compositions are known in the art of microelectronic package manufacture they cannot indiscriminantly be used in this application since they, by definition, will erode the bulk of the copper. Such etchants include copper or ferric chlorides, chromium salts, alkaline-ammonia, hydrogen peroxide-sulfuric acid or nitric acid compositions, and persulfate salts. Each of these compositions has certain  
10 limitations and disadvantages as described hereinbelow.

The metal etchants, in particular the chromium salts, create a deleterious environmental impact. It is also known that chromium salts are human carcinogens; therefore, their use and disposal are especially problematic.

Nitric acid, either alone or in combination with sulfuric acid or copper nitrate, has  
15 been reported by Brittey (United States Patent No. 4,695,348) to be useful for etching copper in wiring boards. However, nitrous oxide gas is a byproduct of this process.

The alkaline-ammonia compositions are used commercially because they are relatively fast, have substantial copper-carrying capacity and are reasonably tolerant of some metal resists and some dry film resists. However, these same compositions have  
20 poor selectivity for copper versus other metals and alloys. Significant process control is required to achieve acceptable selectivity. It is also known that these compositions may not work well with fine line copper geometries. Furthermore, the dissolved copper is

difficult to recover. Also, fumes from the ammonia composition present worker exposure concerns.

The hydrogen peroxide-sulfuric acid compositions, generating permonosulfuric acid, used in copper etching processes are very clean to operate and can be recycled.

5 However, these same compositions have relatively slow etching rates and require substantial cooling for stability control due to the autodecomposition reaction of the hydrogen peroxide. Additionally, both the performance of the process and the decomposition of the peroxide are very sensitive to trace impurities via homo- or hetero-catalysis. Stabilizers are necessary for peak performance but these are metal specific.

10 Brasch (US Patent No. 4,378,270) teaches phenol-sulfonic acid for copper containing solutions. It is also known from Alderuccio, et al (US Patent No. 3,269,881) that these compositions are adversely affected by chloride or bromide ion at levels of 2mg/liter, causing reduced etch rates. Elias (US Patent No. 4,130,455) teaches that the addition of sodium or potassium thiosulfate can counteract this effect.

15 But use of these additives does not address the basic problem of the catalytic decomposition of the peroxide discussed hereinabove. This decomposition has two important implications: firstly, the depletion of the peroxide in the etchant solution reduces the etchant rate; and secondly, there is potential for uncontrolled decomposition of large volumes of high temperature solutions, generating high concentrations of oxygen

20 and increasing the safety risks therefrom. Because decomposition of the peroxide is accelerated at elevated temperatures, processing temperatures must be kept low. This adversely affects the rate of the etching process and exacerbates the already low copper-carrying capacity of the peroxide-sulfuric acid composition.

Another problem associated with using aqueous acidic solutions of hydrogen peroxide for microetching is that it typically requires a two step process. After the treatment step, a further step with diluted sulfuric acid or diluted hydrochloric acid is required due to formation of oxide films on the copper surface.

5 Tytgat and Magnus report in US 4,981,553 that a combination of hydrogen peroxide, chloride ions, phosphoric acid, and phosphate and hydrogenphosphate ions, in quantities to impart a pH of 1.25 to 3, may be used as a copper polishing formulation not requiring excess working temperatures or intense mechanical agitation, however; the process under these conditions is designed to take one or more hours to obtain adequate results. Tytgat et al report that the chloride ion is added for the purpose of protecting the metal against uncontrolled local corrosion and the phosphate ions are added to maintain the desired pH range (i.e., it is added as a buffer). There is no mention or indication that the phosphate ions can function to inhibit etching of other metals in the vicinity of the copper, nor is there teaching that other oxidants can be used in this invention.

15 Heretofore salts of persulfate have been utilized for microetching purposes. Ammonium persulfate, however, is defective in that copper ammonium complex is formed during neutralization making it difficult to remove copper from the wastewater effluent. Prior art studies indicate that sodium persulfate is inferior to ammonium persulfate as a microetchant and furthermore has a short life.

20 Another problem typically encountered with chemical microetching and etching formulations is the tendency for accelerated microetching of copper to occur in regions adjacent to, or in the vicinity of, precious metal, noble or more inert metals such as gold or palladium and their alloys or nickel and its alloys especially nickel/phosphorous. This

effect known as galvanic etching causes undercutting especially of fine line copper circuitry and in worst cases can completely erode the circuit line. Examples of microelectronic packaging where this can occur include printed wiring boards containing plated through holes, edge connectors, etch masks, commoning bars or embedded resistors comprising nickel/phosphorous alloy resistors.

Conventional microetch formulations such as persulfate/sulfuric acid used for cleaning of copper circuits (i.e., printed circuit cards and boards) in the presence of discrete nickel/gold features (i.e., plated contact tabs or edge fingers), or other precious metals can lead to complete etch out of the copper circuit lines due to the galvanic accelerated etch effect associated with these prior art microetchants in the presence of these precious metals. In fact, when multiple microetch cleaning passes are employed it is common to have the copper circuit features completely etched away in as few as 2-3 cleaning passes.

The long-standing problem of galvanic etching has limited the designs and capabilities of the microelectronic packages and has required additional manufacturing complexity in order to circumvent this problem. For example, one prior art attempt to solve the problem of galvanic etching was to apply a soldermask or protective coating over the interface of the gold plated tabs that were attached to the copper circuit lines. However when the soldermask is brought closer to the gold plated connector, there is a higher probability of causing a plugging problem due to flaking or abrading soldermask.

An example of a limitation in PWB design due to galvanic etching is found during the process of microetching of printed wiring boards using conventional microetchants such as acidic persulfate solutions, undercutting of the nickel/copper interface causes the

resultant nickel-clad copper circuit lines to have an uneven cross-section. This defect limits the minimum size of the circuit line and, in doing so, prevents the design of more dense circuits in the printed board package.

Another example of this problem occurs on printed wiring boards having gold plated edge connectors. These gold fingers are typically connected by 0.006" (6 mil) wide copper traces to the rest of the wire board. Prior to shipping the finished wire board, the board is processed through an "ENTEK" process (ENTEK is a trademark of Ethone OMI) consisting of degreaser, prior art sodium persulfate microetch and ENTEK to prepare the copper lands for Surface Mount Technology (SMT) assembly. Boards have frequently been prepared after this "ENTEK" process, in which the copper circuit lines connecting the gold tabs have been completely, or nearly completely, etched through due to galvanic etch effects.

Yet another example of the deleterious effect of prior art microetchants is the degradation of embedded resistor tolerances. Buried or embedded resistors are frequently formed on internal layers of PWB using OHMEGA-PLY Resistor/Conductor Foil. Resistors are formed by selective etching of copper circuit lines and the NiP alloy of the resistors. Precision resistor fabrication requires precise control of resistor dimensions (length, width, and thickness). Good resistor precision and uniformity has been achieved on the etched resistors alone, however, this precision and uniformity is frequently lost as these internal layers with resistors are fabricated into the composite wiring board. The resistor precision is lost while preparing the copper surfaces for laminant bond adhesion using a copper oxide or chlorite process. One example of such a process is the Shipley Chlorite process. The first step in the Shipley Chlorite process is a sodium persulfate/sulfuric acid microetch

step. The purpose of this microetch is to remove copper oxides and to provide a roughened or microetched copper surface. The microetch step is critical for achieving adequate inner laminant bond strengths. However, this particular microetch chemistry etches NiP alloys almost as aggressively as it etches copper and thus the NiP resistors are attacked, causing significant increases in resistor value and tolerance.

Mechanical microetching has also been employed in the past but especially with miniaturization the components in the package become more susceptible to physical damage and contamination. This is especially true when pumice is used, it is not uncommon to find retained pieces entrapped in the copper foil or in the case of scrubbing using nylon brushes, find gouges in the foil surfaces. In addition, thinner innerlayer materials are susceptible to other defects and damage from aggressive mechanical surface scrubbing, such as distortion and incomplete treatment of copper surfaces due to worn scrubbers or plugged nozzles. Due to these problems substitution to chemical polishing is highly desirable.

## SUMMARY OF THE INVENTION

With consideration of the aforementioned problems of cleaning the copper surfaces of microelectronic packaging, the present invention provides for novel formulations, and processes of manufacture of microelectronic packages, in particular printed wiring boards, having the following advantages:

a) a rapid and reproducible manufacturing process for the removal of particulate or film impurities adsorbed on the surfaces of copper elements on a microelectronic

package;

b) printed wiring boards formed having a high density of excellent quality fine line electrical circuits (i.e., uniform line widths) via a high yielding process;

5 c) printed wiring boards having superior adhesion between copper surfaces and dielectric materials, resins, etchmasks, etch resists, solder resists, photoresists and electroplated and electrolessly plated noble metals,

d) a process to selectively clean the surface of copper features in a microelectronic package without causing etching of nickel or nickel phosphorous resistor elements,

10 e) a process to selectively clean the surface of copper features in the proximity of precious metal plated features in a microelectronic package without causing galvanic etching of the bulk copper in the copper features, and

f) a stable, environmentally acceptable, and non-hazardous microetchant formulation.

15 The microelectronic packages fabricated with the use of the inventive formulation may be double sided or be multilayered having inner circuitry layers separated by resin layers and may optionally contain such features as metallized plated through-holes, contact fingers, connecting pads, and planar resistors. The inventive formulations may be used on copper surfaces during the fabrication of printed wiring boards either in the absence of inert metal features, for example to remove oxide coatings on the copper prior  
20 to a solder level process or prior to mounting of electronic parts in order to improve

solderability, or in the presence of inert metal features, for example to clean the surface of copper tabs after electroplating with Ni/Au. In the former example, the function of the inventive formulation is to improve adhesion of the solder. In the latter example, it is to clean the surface while not causing accelerated etching of the copper feature. The present  
5 formulations can be used to improve adhesion between copper surfaces and coating layers of metals, organic resists, dielectric materials, masking materials, or the like. Although not wishing to be bound by theory, it is believed that the current formulation improves adhesion of copper surfaces to solders and other materials by not only cleaning the surface of the copper but also by micro-roughening the surface. This micro-pitting  
10 creates a textured surface that provides greater surface area between the two components.

The current invention can be used during intermediary and final steps in the fabrication of microelectronic packages, in particular, printed wiring boards prepared by either the subtractive, semiadditive or additive process.

It is especially desirable to utilize this inventive microetchant process to fabricate  
15 high density microcomponents having selectively plated Ni/Au features since there is a greater likelihood of galvanic etching of the copper fine line circuitry occurring during this process.

It is also especially desirable to utilize this inventive microetchant process to fabricate microelectronic packages containing both copper features and nickel or  
20 nickel/phosphorus resistors since minimal etching of the nickel or nickel phosphorous resistor is observed.

The invention described herein is a persulfate microetchant composition useful for removing particulate and film forming impurities on the surface of copper features during



fabrication of microelectronic packages. The microetchant is especially characterized by its ability to selectively clean the surface of copper in the presence of nickel or nickel-alloys which may themselves be optionally overplated with noble metal alloys. Prior art references differentiate the "cleaning" of a copper surface as removal of the top 1-5  
5 micron of the copper feature compared to "etching" where removal of bulk copper causes gross changes in dimension to the copper feature. This distinction is maintained in the current invention. Furthermore, in the presence of noble or precious metals no deleterious galvanic etching occurs in this etchant-substrate system so that substantially no accelerated etch of the copper features occur. The combination of high selectivity and  
10 lack of galvanic etch permits multiple cleaning operations during the intermediary steps of microelectronic fabrication process without significant deterioration of the fine line copper circuitry especially in higher density circuits. The persulfate microetchant composition is stabilized with acid and phosphate salts to provide a process that is stable, fast acting, environmentally acceptable, has high capacity, and can be performed at room  
15 temperature. Working microetchant compositions include 25-150 gm/liter sodium persulfate, 0-5% volume % phosphoric acid and 0-0.25 molar sodium phosphate dibasic. Preferred compositions include 50-100 gm/liter sodium persulfate, 1-3% by volume phosphoric acid and 0.05 to 0.15 molar sodium phosphate dibasic.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENT

20 As discussed hereinabove, the invention involves formulating a composition and a process for cleaning or microetching copper or copper alloys. In its most general sense, this inventive process will clean the exposed surfaces of three dimensional copper

objects. These objects can be formed by any manufacturing process and include all crystalline forms of copper. If the copper to be cleaned by this inventive composition is a thin film, it may have been formed from preparation of a rolled copper foil, electroless deposition, electrolytic deposition, or sputtering. The copper may be affixed directly to a core substrate such as epoxy-glass resin, polyethyleneterephthalate, polyimide or other known dielectric materials. In a preferred embodiment, the copper is affixed to the substrate via an adhesion promoting layer which is sandwiched between the copper and the substrate. Compositions known in the art to promote adhesion between the copper and the substrate are, for example, palladium alloy seeds.

The microetchant composition has a unique combination of properties. The chemicals that comprise this formulation are readily available and inexpensive. In addition, the formulation has excellent shelf life and does not pose significant environmental or safety problems. The formulation, although designed to specifically microetch copper features selectively in the presence of inert metals, has wide applicability during many stages of the fabrication of microelectronic packages as seen in the examples hereinbelow. These formulations can be used during the fabrication of printed wiring boards prepared by either the well known subtractive, semi-additive or fully additive processes. The formulations of this invention have been unexpectedly found to eliminate galvanic etching of copper features when such copper features are electrically coupled to nickel (Ni) or nickel/gold (Ni/Au) plated features. The microetchant is selective to cleaning copper without etching nickel or its alloys. The formulations also are selective for etching copper in the presence of other metal etch masks such as solder (Sn/Pb).

The microetchant composition of the present invention comprises a mixture of a

proton donor, a persulfate salt, and a phosphate salt.

The proton donor materials useful in this invention include the strong and weak oxoacids, examples of which include sulfuric acid, phosphoric acid, phosphorous acid, perchloric acid, perchlorous acid and water soluble organic acids such as acetic acid, carbonic acid and oxalic acid. Also contemplated within the scope of the invention are derivatives of the above acids that readily hydrolyze to these acids under ambient or elevated temperatures, such as ester and anhydride derivatives. Other examples include di- and tri-phosphoric acid, polyphosphoric acid, metaphosphoric acid, cyclotrimetaphosphoric acid. The preferred acid is phosphoric acid. Hydrochloric acid and nitric acid, although useful, are not preferred in the current invention due to toxic byproducts such as nitrogen oxides and chlorine gas.

The persulfate salts, also known in the art as peroxydisulfate salts, can be any of the alkali metal or alkaline metal salts that are of sufficient water solubility to prepare the specified formulations. Ammonium persulfate is also a useful salt in this invention. Preferred salts are potassium and sodium persulfate. The most preferred salt is sodium persulfate.

The phosphate salts useful in this composition include alkali metals such as lithium, sodium and potassium phosphate and quaternary nitrogen salts such as ammonium and water soluble alkaline metal phosphate salts. Because the phosphate salt is tribasic, these salts can be either mono, dibasic or tribasic (e.g.,  $\text{NaH}_2\text{PO}_4$ ,  $\text{Na}_2\text{HPO}_4$  and  $\text{Na}_3\text{PO}_4$ ). As known in the art,  $\text{Na}_3\text{PO}_4$  is called sodium orthophosphate and is derived from the reaction of orthophosphoric acid,  $\text{H}_3\text{PO}_4$ , and three equivalents of sodium hydroxide. It is also within the scope of the invention to employ water stable polyphosphate salts such as

diphosphoric acid tetrabasic, and sodium tripolyphosphate as equivalent to the orthophosphate salts. The preferred salts are potassium and sodium phosphate dibasic. Phosphate salts have been utilized in the prior art as a protectant against corrosion; specifically with regard to steel. Phosphoric acid is also known to be added to etchant solutions on which solder (tin-lead) is employed as an etch resist. But no mention is found for the specific combination of phosphate-containing etchants in the presence of nickel. To the contrary, it has been reported that aerated phosphoric acid will corrode nickel. It is therefore an unexpected benefit that in addition to stabilizing the persulfate salt formulation, complete selectivity for etching copper in the presence of nickel is obtained. Although not wishing to be bound by theory, it is believed that the phosphate salts play several important roles in the process including, acting to buffer and stabilize the inventive microetchant formulation, prevent oxide formation from forming on the fresh copper surfaces and prevent attack by the microetchant on the nickel/phosphorous surfaces.

The initial microetchant composition can comprise a mixture of 20-150 gm/liter persulfate salt, up to 5 volume % of the proton donor and up to approximately 0.116 molar phosphate salt. If no phosphate salt is initially included, the composition will rapidly degrade during use (e.g., during the microetching process). Therefore, phosphate salt must be added during the process by adding a regeneration solution of phosphate to bring the working formulation to the desired phosphate concentration. This concentration has been found to unexpectedly give complete stability to the persulfate formulation without any deleterious side effects.

Adjuvants such as surfactants can also have beneficial effects for the etchant formulation. As examples of the classes of surfactants, anionic surfactants, such as carboxylic acid type, polycarboxylic acid type, naphthalene sulfonic acid type and neutral

phosphate type surfactants can be used. Nonionic surfactants and cationic surfactants may also be used depending on conditions of dispersion. Since the pH of the microetchant formulation will be acidic, surfactants of the cationic and anionic type are useful within the scope of the invention. The surfactants range from about 0.001% to about 10% by weight of the formulation, preferably from about 0.01% to 3% by weight. The surfactants alone or in combination, preferably encompass nonionic and anionic surfactants. Examples of nonionic surfactants include without limitation: ethoxylated nonyl and octylphenols of ethylene oxide from 3 to 30 moles of ethylene oxide, and modified polyethoxylated straight chain alcohols as are available under the tradename Triton DF-16 from Rohm & Haas; alkyl polyoxyalkylene ether, (e.g., Mazawet DF from Mazer Chemical) and block copolymers of ethylene oxide and propylene oxide such as Pluronic 31R1 from BASF. Anionic surfactants include without limitation: sulfonated aryl and alkyl hydrocarbon such as Petro BA from Desoto Inc.; sulfated aryl and alkyl hydrocarbons such as Sipon BOS from Alcolac, Inc., FC-135 anionic fluorochemical surfactant from 3M Corporation, and phosphate esters such as Triton H-66 from Rohm & Haas.

Other useful components that can be optionally added to the inventive formulation or used in a prior or subsequent step include, organosilane plated through hole conditioners, buffers, anti-tarnishing agents such as triazoles and polymers to prevent excessive etching such as polyvinyl pyrrolidinone.

In order to improve the adhesiveness between the surfaces of the copper and resin coatings such as prepregs, it is possible to further treat the surfaces (after treatment with the inventive microetching formulation) with an aqueous solution of azole compound or

an alcoholic solution according to U.S. Patent No. 3,645,772. An oxidizing treatment known in the art as brown oxide or black oxide treatment may also be applied after the inventive microetch application.

Organic solderability preservatives react with all copper surfaces that are exposed to the preservative for the purpose of preserving or enhancing solderability of areas that will later be soldered. A typical solderability preservative is benzotriazole, which complexes with copper to form copper triazoles. These copper triazoles inhibit the formation of copper oxides which could adversely affect solderability.

The microetchant process is preferably performed at room temperature, but can also be performed at higher temperatures if desired, up to 130°F. The persulfate microetchant formulations are preferably applied to the component by spraying, but immersion of the component in the formulation is feasible. The contact time between the copper surfaces and the microetchant solution will vary according to the extent of microetch desired, temperature, and specific formulation, but typically will range from about 10 seconds to 10 minutes and preferably between 30 to 120 seconds.

The microetchant formulations are specifically designed to clean the surface or microetch copper in the presence of nickel, nickel-phosphorous or nickel-phosphorous overcoated with noble metals such as gold and palladium. It is also possible to use this microetchant solution with other metal masks, such as solder (Sn/Pb). However, as noted hereinabove, the present formulation can be used satisfactorily to clean copper features when no inert metallic features are present on the microelectronic component.

The inventive microetchant formulation can be widely used for chemical cleaning

and the like for copper or copper alloys. The resulting surfaces of copper have adequate irregularities or "micropitting" with deep concave and convex portions so that they can exhibit excellent adhesion to resins such as prepregs, solder resists, dry film resists, electrodeposited resists and furthermore provides improved solderability. The microetch formulation is, therefore, particularly useful for the manufacture of various PWB, including those for pin grid array (PGA) and ball grid array (BGA), as well as surface treatment of lead frames used for integrated circuit boards.

The dielectric substrates used in the manufacture of the printed wiring boards of this invention can be chosen from a wide range of materials including, ceramics, glass-epoxy, glass cloth reinforced or unreinforced thermoset resins, specifically phenolic resins such as ABS, polyimides such as KAPTAN (a DuPont trademark), polymeric vinyl chloride and TEFLON (a DuPont trademark) and thermosetting and thermoplastic resins such as aromatic polyesters, polyamides, polyacetals, polyarylene sulfides, polyphenyleneoxide, polyimides, polyhaloethylenes, polyether ketones and polyarylates and compositions therefrom. Preferred substrates compositions include polyethyleneterphthalate, polytetrafluoroethylene (Teflon), FR4 epoxy/glass cloth, IBM Driclad epoxy/glass cloth, and BT resins. Where multilayer microelectronic packages are being manufactured by this inventive process, dielectric materials used in the upper strata can also be selected from the abovementioned materials or other dielectric resins known in the art. Therefore, it is considered within the scope of the invention that upper dielectric strata may be composed of the same or different dielectric material as the substrate.

The function and advantage of these and other embodiments of the present invention will be more fully understood from the examples below. The following

examples are intended to illustrate the benefits of the present invention, but do not exemplify the full scope of the invention.

### Working Examples

#### Example 1

5           An example of a generic method employing the present microetchant formulation invention to intermediary manufacturing stages and the final fabrication step of a printed wiring board (PWB) having a Ni/Au plated edge connector, includes the steps of;

10           1) Fabricate a copper laminate on a dielectric substrate, examples of suitable dielectric substrates are given hereinabove, using a homogeneous copper foil preferably 1/2 ounce or less in thickness for internal circuit layers. For the purposes of definition and description: the dielectric substrate, if in the form of a film, will have an uppermost (and outermost) lateral surface that resides above the lowermost (and also outermost) lateral surface by the thickness of the film; additional layers coated on said uppermost lateral surface of said dielectric film will have associated with their coating, an uppermost and lowermost surface, said uppermost layer of said coating being furthest removed from  
15           said uppermost lateral surface of said dielectric film.

            2) Drill and plate through-holes, drilling can be either mechanically performed or optically performed using a laser. Plating can be performed by either sputter, electroless or electrolytically.

20           3) Etch external circuits and commoning bar via standard subtractive processing methods, this step includes the application of a resist, followed by exposure,



development, etch, and finally, strip the resist;

4) Apply a gold plating photoresist mask;

5) Expose and develop the photoresist to uncover copper tabs (features) to be Ni/Au plated;

5 6) Plate electrolytically Ni/Au on exposed copper tabs;

7) Strip photoresist;

8) Apply microetch formulation to clean boards;

9) Apply soldermask, then image, develop, and cure;

10 10) Microetch to clean copper surfaces and ENTEK process to produce copper oxide surfaces;

11) Profile cards from panel; and

12) Reclean with microetchant formulation as required.

15 Steps 8), 10), and 12) involve cleaning with a microetchant formulation. If prior art persulfate/sulfuric acid microetchant is used significant bulk etching of the copper due to galvanic etching is observed. Replacement with the inventive formulation of sodium persulfate 100gm/L, 3% phosphoric acid, and 0.058M sodium phosphate salt eliminates galvanic etching. Specifically contemplated as part of the present invention is the use of

the inventive microetchant formulation during appropriate intermediary manufacturing steps 1-11 and final fabrication step, step 12.

### Example 2

Manufacture of an embedded resistor PWB, involves the following steps:

- 5           1) Laminate copper and OHMEGA-PLY resistor/conductor (a copper/nickel laminate) foil to a dielectric material such as epoxy-glass,
- 2) Apply a resist, followed by exposing, developing the conductor/resistor pattern,
- 3) Etch the copper circuits in any typical etchant (e.g., cupric chloride, ferric chloride, ammoniacal etch, etc.),
- 10          4) Etch exposed nickel/phosphorous, NiP resistive element, in  $\text{CuSO}_4$  etchant,
- 5) Strip the photoresist,
- 6) Apply a second photoresist, expose and develop the resistor pattern,
- 7) Selectively etch copper, leaving the NiP resistor behind. This step may be performed in chrome-sulfuric, ammoniacal etch solutions or a persulfate/phosphoric acid/phosphate salt etchant disclosed in a co-pending, commonly owned, United States
- 15          Patent Application: Serial no. 09/165,957, filed 10/2/98 by Lauffer, et al., entitled Copper Etching Compositions, Processes, and Products Derived Therefrom,

8) Strip the photoresist,

9) Test the resistors,

10) Use the Shipley Chlorite process for multilayer lamination. All commercially available oxide or adhesion treatment chemistries include a copper microetch consisting of sodium persulfate/sulfuric acid as a first copper preparation step,

11) Perform multilayer lamination,

12) Composite drill, plate and etch,

13) Apply a protective coat/soldermask and process, and

14) Final test including shorts/opens and resistor values.

Parts fabricated using the above process had significant resistor value mean and tolerance shifts occur between steps 9 and 14, that was predominantly due to the copper microetch chemistry of step 10. OHMEGA-PLY 25ohm/square material processed as above had resistor mean and tolerance shifts of approximately 1.2-1.3X between steps 9 and 14. OHMEGA-PLY 100ohm/square material processed as above had resistor mean and tolerance shifts of approximately 4-5X between steps 9 and 14. Using the inventive microetch formulation containing 100gm/liter sodium persulfate, 3 volume % phosphoric acid and 0.058 molar sodium phosphate, in step 10, effective removal of the copper oxide film and microetch of copper was obtained with no attack on the NiP resistor. In this case both OHMEGA-PLY 25 and

100 ohm/square materials had less than 5% resistor mean and less than 2% resistor tolerance shifts when processed with this chemistry.

### Example 3

A process of manufacturing a printed wiring board having selectively plated nickel/gold features comprising the steps of:

a) providing a dielectric substrate having at least one outermost lateral surface;

b) fabricating a layer of copper to said at least one said outermost lateral surface of said dielectric substrate (fabrication can include such processes as sputtering, lamination of copper foil, electroplating and electroless plating and the like);

c) drilling through said copper layer and said dielectric substrate to form through-holes having vertical walls (drilling can include such processes as mechanical drilling using a bit or optical drilling such as with a laser);

d) plating copper on said vertical walls of said through-holes and outermost copper surface of said laminated copper foil, creating a layer of plated copper having an outermost surface (plating can be performed by any of the processes described in step (b));

e) applying a resist to said outermost surface of said plated copper (application of the resist can be performed by dipping, laminating, spraying or spinning and the like; the resist itself can be either in solid layer form or in liquid form, furthermore, the resist can be either negative working or positive working);

f) exposing and developing said resist and etching uncovered plated copper and said underlying copper layer, thereby fabricating on said outermost surface of said dielectric substrate, multiple, independent external circuits and a commoning bar connected thereto, said external circuits and said commoning bar each having an outermost surface;

5 g) stripping said developed resist;

h) applying a plating photoresist mask to said outermost surfaces of said multiple, independent external circuits, said commoning bar and uncovered areas of said outermost surfaces of said dielectric substrate;

10 i) exposing and developing said plating photoresist mask to uncover select copper features from said external circuits, said select copper features having outermost lateral and vertical side surfaces;

j) plating nickel/gold on said uncovered outermost lateral and vertical side surfaces of said select copper features (the plating process can be any of the processes described in step (b));

15 k) stripping said developed plating photoresist mask that was exposed and developed in step (i), uncovering unplated copper external circuits and portions of said uppermost surface of said dielectric substrate, and said uncovered plated through-holes;

l) applying a microetch aqueous solution comprising an inorganic acid, a persulfate salt and a phosphate salt, to clean said unplated copper external circuits and

said plated through-hole walls of in-process oxides and other contaminants from Step k,(tank processing which is used for oxide pre-cleans, or pre-plate cleaning operations are performed using microetchant solutions at about 80-90°F, and a dwell time from about 15 seconds to 2 minutes depending on the particular application, pre-oxide cleaning typically is performed with a 15 second dwell time);

m) applying a solder mask to said outermost surfaces of said external circuits, said nickel/gold plated copper features, said plated through-holes and said commoning bar;

n) imaging, developing, and curing said solder mask applied in step (m) to expose said plated through holes and outermost surfaces of said external circuits and nickel/gold plated copper features;

o) reapplying said microetch aqueous solution comprising an inorganic acid, a persulfate salt and a phosphate salt, to clean in-process oxides and other contaminants (conveyorized spray processing for end of line cleaning prior to solderability preservative application can be performed at about 80-90°F with a spray pressure of about 15-20 psi, and a dwell time of 20-30 seconds);

p) applying an organic solderability preservative to said walls of said plated through-holes, said outermost surfaces of said external circuits, said nickel/gold plated copper features, and other said uncovered non-nickel gold plated copper features;

q) separating said external circuitry from said commoning layer, creating individual printed wiring boards; and

r) reapplying said microetch aqueous solution comprising an inorganic acid, a persulfate salt and a phosphate salt, to clean said individual printed wiring boards.

#### Example 4

5 A process to manufacture an embedded resistor printed wiring board, comprising the steps of:

a) providing a dielectric substrate having at least one outermost lateral surface;

10 b) providing a laminate copper/resistive foil, comprising a copper layer having an uppermost, smooth surface, and a lowermost, rough surface, and a nickel resistive layer having an uppermost and lowermost surface, said lowermost, rough copper surface and said uppermost nickel resistive surface being in intimate contact, the assembled laminate copper/resistive foil having an uppermost copper surface and a lowermost nickel resistive surface;

c) laminating said lowermost nickel resistive surface of said laminate copper/resistive foil to said outermost lateral surface of said dielectric substrate;

15 d) applying a first photoresist to said uppermost copper surface of said laminate copper/resistive foil;

e) exposing and developing said first photoresist, thereby uncovering discrete areas of said uppermost surface of said laminate copper/resistive foil;

f) etching in a subtractive process said discrete, uncovered areas of said copper

layer, thereby fabricating copper fine line circuitry in covered areas, and uncovering said uppermost surface of said nickel resistive layer in said etched areas, said copper fine line circuitry having an uppermost surface and vertical side walls;

g) etching said uncovered areas of said nickel resistive layer in electrical contact with said copper fine line circuitry using a copper sulfate/sulfuric acid etch solution;

h) stripping said developed first photoresist;

i) applying a second photoresist to the uppermost surface and vertical side walls of said copper fine line circuitry and said outermost dielectric substrate;

j) exposing and developing a resistor pattern into said second photoresist, uncovering second discrete areas of said uppermost surface of said laminate copper/resistive foil;

k) selectively etching copper from said second uncovered discrete areas of said laminate copper/resistive foil, while leaving underlying areas of said nickel resistive layer unaffected, thereby forming nickel resistive elements having uppermost and side wall surfaces;

l) stripping said developed second photoresist;

m) applying a microetch aqueous solution comprising an inorganic acid, a persulfate salt and a phosphate salt, to clean said copper fine line circuitry;



n) enhancing bond strength to subsequently applied dielectric materials by using a chlorite or copper oxide process for multilayer lamination, whereby copper oxide is formed on said uppermost surface and side walls of said copper fine line circuitry;

5 o) applying a second dielectric layer to the uppermost surface and side walls of said fine line copper circuits, to said uppermost surface and side walls of said nickel resistive elements, and to said uncovered outermost surface of said first dielectric substrate, wherein said second dielectric layer has an uppermost surface;

p) modifying said uppermost surface of said second dielectric layer to provide adhesion to subsequent fine line copper circuitry;

10 q) drilling and plating through-holes through said second dielectric layer;

r) fabricating fine line copper circuitry on said uppermost surface of said second dielectric layer by subtractive, semiadditive or additive processes; and

15 s) connecting electrically fine line copper circuitry on said uppermost surface of said second dielectric layer to said fine line copper circuitry and said nickel resistive elements of said first dielectric substrate via said through-holes, forming a composite laminate having an embedded nickel resistor element.

20 Those skilled in the art would readily appreciate that all parameters listed herein are meant to be exemplary and that actual parameters will depend upon the specific application for which methods and apparatus of the present invention are used. It is therefore, to be understood that the foregoing embodiments are presented by way of

example only and that, within the scope of the appended claims and equivalents thereto, the invention may be practiced otherwise than specifically described.

5        Since other modifications and changes varied to fit particular operating requirements and environments will be apparent to those skilled in the art, the invention is not considered limited to the examples chosen for purposes of disclosure, and covers all changes and modifications which do not constitute departures from the true spirit and scope of this invention.

      Having thus described the invention, what is desired to be protected by Letters Patent is presented in the subsequently appended claims.

What is claimed is:

1           1. A process for cleaning copper surfaces of copper objects, without etching bulk  
2 copper from said objects, comprising contacting said surfaces with an aqueous solution  
3 comprising an inorganic acid, a persulfate salt and a phosphate salt.

1           2. The process as recited in claim 1, wherein said objects are copper features on  
2 intermediary and final structures of a microelectronic package, said microelectronic  
3 package comprising a dielectric substrate having at least one lateral outermost surface to  
4 which said copper features are attached.

1           3. The process as recited in claim 1, wherein said phosphate salt is selected from  
2 the group consisting of orthophosphate, metaphosphate, hydrogenphosphate and  
3 dihydrogenphosphate salts.

1           4. The process as recited in claim 3, wherein the cation in said phosphate salt is  
2 selected from the group consisting of ammonium, potassium, sodium, lithium, and water  
3 soluble alkaline metal cations.

1           5. The process as recited in claim 1, wherein said inorganic acid is selected from  
2 the group consisting of sulfuric acid, phosphoric acid, metaphosphoric acid and  
3 pyrophosphoric acid.

1           6. The process as recited in claim 1, wherein the cation in said persulfate salt is  
2 selected from the group consisting of alkali metals, ammonium and water soluble alkaline  
3 metal cations.

1           7. The process as recited in claim 1, wherein said aqueous solution comprises  
2 approximately 25-100 gm/liter sodium persulfate, up to about 3 volume% phosphoric  
3 acid, and up to about 0.116 Molar sodium phosphate.

1           8. The process as recited in claim 1, wherein said aqueous solution further  
2 comprises a surfactant.

1           9. The process as recited in claim 8, wherein said surfactant is anionic.

1           10. The process as recited in claim 9, wherein said anionic surfactant is selected  
2 from the group of compounds consisting of aryl sulfonates, alkyl sulfonates, aryl sulfates,  
3 alkyl sulfates and phosphate esters.

1           11. The process as recited in claim 8, wherein said surfactant is nonionic.

1           12. The process as recited in claim 11, wherein said nonionic surfactant is  
2 selected from the group of compounds consisting of nonyl phenol ethoxylated with 3-30  
3 moles of ethylene oxide, octyl phenol ethoxylated with 3-30 moles of ethylene oxide,  
4 block copolymers of ethylene oxide and propylene oxide, and alkyl polyoxyalkylene  
5 ethers.

1           13. The process as recited in claim 2, wherein said copper features, comprise at  
2 least one of the group consisting of plated through holes, contact fingers, tabs, connecting  
3 pads, and external and fine line circuitry.

1           14. The process as recited in claim 13, wherein said intermediary and final  
2 structures of said microelectronic package further comprise precious metal/nickel or  
3 phosphorous/nickel plated features, wherein said surfaces of unplated said copper features  
4 are proximate said precious metal/nickel or phosphorous/nickel plated features, wherein  
5 said copper surfaces are unaffected by galvanic or accelerated etching of bulk copper  
6 from said aqueous solution.

1           15. The process as recited in claim 14, wherein said precious metal is gold or  
2 palladium.

1           16. The process as recited in claim 2, wherein said intermediary and final  
2 structures of said microelectronic package comprise an embedded nickel resistor.

1           17. A process to manufacture an intermediate structure of an embedded resistor  
2 printed wiring board, comprising the steps of:

3           a) providing a printed wiring board internal core comprising, a dielectric substrate  
4 having at least one outermost lateral surface, copper features, and at least one nickel or  
5 nickel alloy planar resistor formed on said at least one of said outermost lateral surfaces;  
6 and

7           b) applying a microetch solution comprising an inorganic acid, a persulfate salt  
8 and a phosphate salt, to clean exposed surfaces of said copper features, without adversely  
9 affecting the resistor values of said at least one nickel or nickel alloy planar resistor.

18. The process to manufacture an embedded resistor printed wiring board, as described in claim 17, wherein said first and second dielectric substrates are selected from the group consisting of epoxy resins, polyimides, polytetrafluoroethylene (TEFLON), cyanates, cyanate esters, BT epoxies, and IBM Driclad epoxy, either unreinforced or reinforced with glass.

19. A process to manufacture a planar resistor in an intermediate structure printed wiring board, comprising the steps of:

a) providing a printed wiring board internal core comprising a dielectric substrate having at least one lateral outer surface and first copper features affixed to said at least one of said lateral outer surfaces;

b) applying a microetch solution comprising an inorganic acid, a persulfate salt and a phosphate salt, to said first copper features in order to clean exposed surfaces of said first copper features;

c) enhancing bond strength to subsequently applied dielectric materials by forming copper oxide on uppermost and sidewall surfaces of said first copper features;

d) applying a dielectric material to the first dielectric substrate to exposed said lateral outer surfaces of said dielectric substrate and to said first copper features in order to generate a multilayer laminate;

e) fabricating and plating through-holes through said dielectric material;

15 f) forming second copper features and at least one planar nickel or nickel alloy  
 16 resistor on an uppermost surface of said dielectric material, said second copper features  
 17 and said planar resistor being electrically connected to said first copper features through  
 18 said plated through-holes; and

19 g) applying a microetch solution comprising an inorganic acid, a persulfate salt  
 20 and a phosphate salt to said second copper features in order to clean exposed  
 21 surfaces of said second copper features without adversely affecting the resistor values of  
 22 said at least one nickel or planar nickel alloy resistor.

1 20. A process of manufacturing intermediary structures of a microelectronic  
 2 package, comprising the steps of:

3 a) providing a microelectronic package comprising a dielectric substrate, said  
 4 dielectric substrate having an outermost lateral surface with at least one component  
 5 selected from the group consisting of unplated copper features, precious metal plated  
 6 copper features, and copper circuit lines attached thereto;

7 b) applying an aqueous microetchant solution comprising inorganic acid,  
 8 persulfate salt and phosphate salt, to said microelectronic package in order to clean said  
 9 unplated copper features, without causing galvanic etching of bulk copper from said  
 10 components;

11 c) applying and processing a soldermask material to uppermost surfaces of said  
 12 components in order to expose said copper features, while protecting said copper circuit  
 13 lines with unprocessed soldermask material;

14                   d) reapplying said aqueous microetchant solution from step (b), to said copper  
15 features in order to clean in-process oxides and other contaminants without galvanic  
16 etching of bulk copper from said copper features; and

17                   e) applying an organic solderability preservative to said exposed unplated copper  
18 features to fabricate sites for mounting pads.

14  
15  
16  
17  
18  
19  
20  
21  
22  
23  
24  
25  
26  
27  
28  
29  
30  
31  
32  
33  
34  
35  
36  
37  
38  
39  
40  
41  
42  
43  
44  
45  
46  
47  
48  
49  
50  
51  
52  
53  
54  
55  
56  
57  
58  
59  
60  
61  
62  
63  
64  
65  
66  
67  
68  
69  
70  
71  
72  
73  
74  
75  
76  
77  
78  
79  
80  
81  
82  
83  
84  
85  
86  
87  
88  
89  
90  
91  
92  
93  
94  
95  
96  
97  
98  
99  
100  
101  
102  
103  
104  
105  
106  
107  
108  
109  
110  
111  
112  
113  
114  
115  
116  
117  
118  
119  
120  
121  
122  
123  
124  
125  
126  
127  
128  
129  
130  
131  
132  
133  
134  
135  
136  
137  
138  
139  
140  
141  
142  
143  
144  
145  
146  
147  
148  
149  
150  
151  
152  
153  
154  
155  
156  
157  
158  
159  
160  
161  
162  
163  
164  
165  
166  
167  
168  
169  
170  
171  
172  
173  
174  
175  
176  
177  
178  
179  
180  
181  
182  
183  
184  
185  
186  
187  
188  
189  
190  
191  
192  
193  
194  
195  
196  
197  
198  
199  
200  
201  
202  
203  
204  
205  
206  
207  
208  
209  
210  
211  
212  
213  
214  
215  
216  
217  
218  
219  
220  
221  
222  
223  
224  
225  
226  
227  
228  
229  
230  
231  
232  
233  
234  
235  
236  
237  
238  
239  
240  
241  
242  
243  
244  
245  
246  
247  
248  
249  
250  
251  
252  
253  
254  
255  
256  
257  
258  
259  
260  
261  
262  
263  
264  
265  
266  
267  
268  
269  
270  
271  
272  
273  
274  
275  
276  
277  
278  
279  
280  
281  
282  
283  
284  
285  
286  
287  
288  
289  
290  
291  
292  
293  
294  
295  
296  
297  
298  
299  
300  
301  
302  
303  
304  
305  
306  
307  
308  
309  
310  
311  
312  
313  
314  
315  
316  
317  
318  
319  
320  
321  
322  
323  
324  
325  
326  
327  
328  
329  
330  
331  
332  
333  
334  
335  
336  
337  
338  
339  
340  
341  
342  
343  
344  
345  
346  
347  
348  
349  
350  
351  
352  
353  
354  
355  
356  
357  
358  
359  
360  
361  
362  
363  
364  
365  
366  
367  
368  
369  
370  
371  
372  
373  
374  
375  
376  
377  
378  
379  
380  
381  
382  
383  
384  
385  
386  
387  
388  
389  
390  
391  
392  
393  
394  
395  
396  
397  
398  
399  
400  
401  
402  
403  
404  
405  
406  
407  
408  
409  
410  
411  
412  
413  
414  
415  
416  
417  
418  
419  
420  
421  
422  
423  
424  
425  
426  
427  
428  
429  
430  
431  
432  
433  
434  
435  
436  
437  
438  
439  
440  
441  
442  
443  
444  
445  
446  
447  
448  
449  
450  
451  
452  
453  
454  
455  
456  
457  
458  
459  
460  
461  
462  
463  
464  
465  
466  
467  
468  
469  
470  
471  
472  
473  
474  
475  
476  
477  
478  
479  
480  
481  
482  
483  
484  
485  
486  
487  
488  
489  
490  
491  
492  
493  
494  
495  
496  
497  
498  
499  
500  
501  
502  
503  
504  
505  
506  
507  
508  
509  
510  
511  
512  
513  
514  
515  
516  
517  
518  
519  
520  
521  
522  
523  
524  
525  
526  
527  
528  
529  
530  
531  
532  
533  
534  
535  
536  
537  
538  
539  
540  
541  
542  
543  
544  
545  
546  
547  
548  
549  
550  
551  
552  
553  
554  
555  
556  
557  
558  
559  
560  
561  
562  
563  
564  
565  
566  
567  
568  
569  
570  
571  
572  
573  
574  
575  
576  
577  
578  
579  
580  
581  
582  
583  
584  
585  
586  
587  
588  
589  
590  
591  
592  
593  
594  
595  
596  
597  
598  
599  
600  
601  
602  
603  
604  
605  
606  
607  
608  
609  
610  
611  
612  
613  
614  
615  
616  
617  
618  
619  
620  
621  
622  
623  
624  
625  
626  
627  
628  
629  
630  
631  
632  
633  
634  
635  
636  
637  
638  
639  
640  
641  
642  
643  
644  
645  
646  
647  
648  
649  
650  
651  
652  
653  
654  
655  
656  
657  
658  
659  
660  
661  
662  
663  
664  
665  
666  
667  
668  
669  
670  
671  
672  
673  
674  
675  
676  
677  
678  
679  
680  
681  
682  
683  
684  
685  
686  
687  
688  
689  
690  
691  
692  
693  
694  
695  
696  
697  
698  
699  
700  
701  
702  
703  
704  
705  
706  
707  
708  
709  
710  
711  
712  
713  
714  
715  
716  
717  
718  
719  
720  
721  
722  
723  
724  
725  
726  
727  
728  
729  
730  
731  
732  
733  
734  
735  
736  
737  
738  
739  
740  
741  
742  
743  
744  
745  
746  
747  
748  
749  
750  
751  
752  
753  
754  
755  
756  
757  
758  
759  
760  
761  
762  
763  
764  
765  
766  
767  
768  
769  
770  
771  
772  
773  
774  
775  
776  
777  
778  
779  
780  
781  
782  
783  
784  
785  
786  
787  
788  
789  
790  
791  
792  
793  
794  
795  
796  
797  
798  
799  
800  
801  
802  
803  
804  
805  
806  
807  
808  
809  
810  
811  
812  
813  
814  
815  
816  
817  
818  
819  
820  
821  
822  
823  
824  
825  
826  
827  
828  
829  
830  
831  
832  
833  
834  
835  
836  
837  
838  
839  
840  
841  
842  
843  
844  
845  
846  
847  
848  
849  
850  
851  
852  
853  
854  
855  
856  
857  
858  
859  
860  
861  
862  
863  
864  
865  
866  
867  
868  
869  
870  
871  
872  
873  
874  
875  
876  
877  
878  
879  
880  
881  
882  
883  
884  
885  
886  
887  
888  
889  
890  
891  
892  
893  
894  
895  
896  
897  
898  
899  
900  
901  
902  
903  
904  
905  
906  
907  
908  
909  
910  
911  
912  
913  
914  
915  
916  
917  
918  
919  
920  
921  
922  
923  
924  
925  
926  
927  
928  
929  
930  
931  
932  
933  
934  
935  
936  
937  
938  
939  
940  
941  
942  
943  
944  
945  
946  
947  
948  
949  
950  
951  
952  
953  
954  
955  
956  
957  
958  
959  
960  
961  
962  
963  
964  
965  
966  
967  
968  
969  
970  
971  
972  
973  
974  
975  
976  
977  
978  
979  
980  
981  
982  
983  
984  
985  
986  
987  
988  
989  
990  
991  
992  
993  
994  
995  
996  
997  
998  
999  
1000  
1001  
1002  
1003  
1004  
1005  
1006  
1007  
1008  
1009  
1010  
1011  
1012  
1013  
1014  
1015  
1016  
1017  
1018  
1019  
1020  
1021  
1022  
1023  
1024  
1025  
1026  
1027  
1028  
1029  
1030  
1031  
1032  
1033  
1034  
1035  
1036  
1037  
1038  
1039  
1040  
1041  
1042  
1043  
1044  
1045  
1046  
1047  
1048  
1049  
1050  
1051  
1052  
1053  
1054  
1055  
1056  
1057  
1058  
1059  
1060  
1061  
1062  
1063  
1064  
1065  
1066  
1067  
1068  
1069  
1070  
1071  
1072  
1073  
1074  
1075  
1076  
1077  
1078  
1079  
1080  
1081  
1082  
1083  
1084  
1085  
1086  
1087  
1088  
1089  
1090  
1091  
1092  
1093  
1094  
1095  
1096  
1097  
1098  
1099  
1100  
1101  
1102  
1103  
1104  
1105  
1106  
1107  
1108  
1109  
1110  
1111  
1112  
1113  
1114  
1115  
1116  
1117  
1118  
1119  
1120  
1121  
1122  
1123  
1124  
1125  
1126  
1127  
1128  
1129  
1130  
1131  
1132  
1133  
1134  
1135  
1136  
1137  
1138  
1139  
1140  
1141  
1142  
1143  
1144  
1145  
1146  
1147  
1148  
1149  
1150  
1151  
1152  
1153  
1154  
1155  
1156  
1157  
1158  
1159  
1160  
1161  
1162  
1163  
1164  
1165  
1166  
1167  
1168  
1169  
1170  
1171  
1172  
1173  
1174  
1175  
1176  
1177  
1178  
1179  
1180  
1181  
1182  
1183  
1184  
1185  
1186  
1187  
1188  
1189  
1190  
1191  
1192  
1193  
1194  
1195  
1196  
1197  
1198  
1199  
1200  
1201  
1202  
1203  
1204  
1205  
1206  
1207  
1208  
1209  
1210  
1211  
1212  
1213  
1214  
1215  
1216  
1217  
1218  
1219  
1220  
1221  
1222  
1223  
1224  
1225  
1226  
1227  
1228  
1229  
1230  
1231  
1232  
1233  
1234  
1235  
1236  
1237  
1238  
1239  
1240  
1241  
1242  
1243  
1244  
1245  
1246  
1247  
1248  
1249  
1250  
1251  
1252  
1253  
1254  
1255  
1256  
1257  
1258  
1259  
1260  
1261  
1262  
1263  
1264  
1265  
1266  
1267  
1268  
1269  
1270  
1271  
1272  
1273  
1274  
1275  
1276  
1277  
1278  
1279  
1280  
1281  
1282  
1283  
1284  
1285  
1286  
1287  
1288  
1289  
1290  
1291  
1292  
1293  
1294  
1295  
1296  
1297  
1298  
1299  
1300  
1301  
1302  
1303  
1304  
1305  
1306  
1307  
1308  
1309  
1310  
1311  
1312  
1313  
1314  
1315  
1316  
1317  
1318  
1319  
1320  
1321  
1322  
1323  
1324  
1325  
1326  
1327  
1328  
1329  
1330  
1331  
1332  
1333  
1334  
1335  
1336  
1337  
1338  
1339  
1340  
1341  
1342  
1343  
1344  
1345  
1346  
1347  
1348  
1349  
1350  
1351  
1352  
1353  
1354  
1355  
1356  
1357  
1358  
1359  
1360  
1361  
1362  
1363  
1364  
1365  
1366  
1367  
1368  
1369  
1370  
1371  
1372  
1373  
1374  
1375  
1376  
1377  
1378  
1379  
1380  
1381  
1382  
1383  
1384  
1385  
1386  
1387  
1388  
1389  
1390  
1391  
1392  
1393  
1394  
1395  
1396  
1397  
1398  
1399  
1400  
1401  
1402  
1403  
1404  
1405  
1406  
1407  
1408  
1409  
1410  
1411  
1412  
1413  
1414  
1415  
1416  
1417  
1418  
1419  
1420  
1421  
1422  
1423  
1424  
1425  
1426  
1427  
1428  
1429  
1430  
1431  
1432  
1433  
1434  
1435  
1436  
1437  
1438  
1439  
1440  
1441  
1442  
1443  
1444  
1445  
1446  
1447  
1448  
1449  
1450  
1451  
1452  
1453  
1454  
1455  
1456  
1457  
1458  
1459  
1460  
1461  
1462  
1463  
1464  
1465  
1466  
1467  
1468  
1469  
1470  
1471  
1472  
1473  
1474  
1475  
1476  
1477  
1478  
1479  
1480  
1481  
1482  
1483  
1484  
1485  
1486  
1487  
1488  
1489  
1490  
1491  
1492  
1493  
1494  
1495  
1496  
1497  
1498  
1499  
1500  
1501  
1502  
1503  
1504  
1505  
1506  
1507  
1508  
1509  
1510  
1511  
1512  
1513  
1514  
1515  
1516  
1517  
1518  
1519  
1520  
1521  
1522  
1523  
1524  
1525  
1526  
1527  
1528  
1529  
1530  
1531  
1532  
1533  
1534  
1535  
1536  
1537  
1538  
1539  
1540  
1541  
1542  
1543  
1544  
1545  
1546  
1547  
1548  
1549  
1550  
1551  
1552  
1553  
1554  
1555  
1556  
1557  
1558  
1559  
1560  
1561  
1562  
1563  
1564  
1565  
1566  
1567  
1568  
1569  
1570  
1571  
1572  
1573  
1574  
1575  
1576  
1577  
1578  
1579  
1580  
1581  
1582  
1583  
1584  
1585  
1586  
1587  
1588  
1589  
1590  
1591  
1592  
1593  
1594  
1595  
1596  
1597  
1598  
1599  
1600  
1601  
1602  
1603  
1604  
1605  
1606  
1607  
1608  
1609  
1610  
1611  
1612  
1613  
1614  
1615  
1616  
1617  
1618  
1619  
1620  
1621  
1622  
1623  
1624  
1625  
1626  
1627  
1628  
1629  
1630  
1631  
1632  
1633  
1634  
1635  
1636  
1637  
1638  
1639  
1640  
1641  
1642  
1643  
1644  
1645  
1646  
1647  
1648  
1649  
1650  
1651  
1652  
1653  
1654  
1655  
1656  
1657  
1658  
1659  
1660  
1661  
1662  
1663  
1664  
1665  
1666  
1667  
1668  
1669  
1670  
1671  
1672  
1673  
1674  
1675  
1676  
1677  
1678  
1679  
1680  
1681  
1682  
1683  
1684  
1685  
1686  
1687  
1688  
1689  
1690  
1691  
1692  
1693  
1694  
1695  
1696  
1697  
1698  
1699  
1700  
1701  
1702  
1703  
1704  
1705  
1706  
1707  
1708  
1709  
1710  
1711  
1712  
1713  
1714  
1715  
1716  
1717  
1718  
1719  
1720  
1721  
1722  
1723  
1724  
1725  
1726  
1727  
1728  
1729  
1730  
1731  
1732  
1733  
1734  
1735  
1736  
1737  
1738  
1739  
1740  
1741  
1742  
1743  
1744  
1745  
1746  
1747  
1748  
1749  
1750  
1751  
1752  
1753  
1754  
1755  
1756  
1757  
1758  
1759  
1760  
1761  
1762  
1763  
1764  
1765  
1766  
1767  
1768  
1769  
1770  
1771  
1772  
1773  
1774  
1775  
1776  
1777  
1778  
1779  
1780  
1781  
1782  
1783  
1784  
1785  
1786  
1787  
1788  
1789  
1790  
1791  
1792  
1793  
1794  
1795  
1796  
1797  
1798  
1799  
1800  
1801  
1802  
1803  
1804  
1805  
1806  
1807  
1808  
1809  
1810  
1811  
1812  
1813  
1814  
1815  
1816  
1817  
1818  
1819  
1820  
1821  
1822  
1823  
1824  
1825  
1826  
1827  
1828  
1829  
1830  
1831  
1832  
1833  
1834  
1835  
1836  
1837  
1838  
1839  
1840  
1841  
1842  
1843  
1844  
1845  
1846  
1847  
1848  
1849  
1850  
1851  
1852  
1853  
1854  
1855  
1856  
1857  
1858  
1859  
1860  
1861  
1862  
1863  
1864  
1865  
1866  
1867  
1868  
1869  
1870  
1871  
1872  
1873  
1874  
1875  
1876  
1877  
1878  
1879  
1880  
1881  
1882  
1883  
1884  
1885  
1886  
1887  
1888  
1889  
1890  
1891  
1892  
1893  
1894  
1895  
1896  
1897  
1898  
1899  
1900  
1901  
1902  
1903  
1904  
1905  
1906  
1907  
1908  
1909  
1910  
1911  
1912  
1913  
1914  
1915  
1916  
1917  
1918  
1919  
1920  
1921  
1922  
1923  
1924  
1925  
1926  
1927  
1928  
1929  
1930  
1931  
1932  
1933  
1934  
1935  
1936  
1937  
1938  
1939  
1940  
1941  
1942  
1943  
1944  
1945  
1946  
1947  
1948  
1949  
1950  
1951  
1952  
1953  
1954  
1955  
1956  
1957  
1958  
1959  
1960  
1961  
1962  
1963  
1964  
1965  
1966  
1967  
1968  
1969  
1970  
1971  
1972  
1973  
1974  
1975  
1976  
1977  
1978  
1979  
1980  
1981  
1982  
1983  
1984  
1985  
1986  
1987  
1988  
1989  
1990  
1991  
1992  
1993  
1994  
1995  
1996  
1997  
1998  
1999  
2000  
2001  
2002  
2003  
2004  
2005  
2006  
2007  
2008  
2009  
2010  
2011  
2012  
2013  
2014  
2015  
2016  
2017  
2018  
2019  
2020  
2021  
2022  
2023  
2024  
2025  
2026  
2027  
2028  
2029  
2030  
2031  
2032  
2033  
2034  
2035  
2036  
2037  
2038  
2039  
2040  
2041  
2042  
2043  
2044  
2045  
2046  
2047  
2048  
2049  
2050  
2051  
2052  
2053  
2054  
2055  
2056  
2057  
2058  
2059  
2060  
2061  
2062  
2063  
2064  
2065  
2066  
2067  
2068  
2069  
2070  
2071  
2072  
2073  
2074  
2075  
2076  
2077  
2078  
2079  
2080  
2081  
2082  
2083  
2084  
2085  
2086  
2087  
2088  
2089  
2090  
2091  
2092  
2093  
2094  
2095  
2096  
2097  
2098  
2099  
2100  
2101  
2102  
2103  
2104  
2105  
2106  
2107  
2108  
2109  
2110  
2111  
2112  
2113  
2114  
2115  
2116  
2117  
2118  
2119  
2120  
2121  
2122  
2123  
2124  
2125  
2126  
2127  
2128  
2129  
2130  
2131  
2132  
2133  
2134  
2135  
2136  
2137  
2138  
2139  
2140  
2141  
2142  
2143  
2144  
2145  
2146  
2147  
2148  
2149  
2150  
2151  
2152  
2153  
2154  
2155  
2156  
2157  
2158  
2159  
2160  
2161  
2162  
2163  
2164  
2165  
2166  
2167  
2168  
2169  
2170  
2171  
2172  
2173  
2174  
2175  
2176  
2177  
2178  
2179  
2180  
2181  
2182  
2183  
2184  
2185  
2186  
2187  
2188  
2189  
2190  
2191  
2192  
2193  
2194  
2195  
2196  
2197  
2198  
2199  
2200  
2201  
2202  
2203  
2204  
2205  
2206  
2207  
2208  
2209  
2210  
2211  
2212  
2213  
2214  
2215  
2216  
2217  
2218  
2219  
2220  
2221  
2222  
2223  
2224  
2225  
2



ABSTRACT OF THE DISCLOSURE  
COPPER COMPOSITIONS, PROCESSES AND PRODUCTS DERIVED THEREFROM

The present invention is a persulfate microetchant composition especially useful for removing impurities from copper surfaces during fabrication of microelectronic packages. The microetchant formulation is characterized by its ability to selectively clean copper in the presence of nickel, nickel-phosphorous and noble metal alloys therefrom. Furthermore, no deleterious galvanic etching occurs in this microetchant-substrate system so that substantially no undercutting of the copper occurs. The combination of high selectivity and no undercutting allows for a simplification of the microelectronic fabrication process and significant improvements in the design features of the microelectronic package, in particular higher density circuits. The persulfate microetchant composition is stabilized with acid and phosphate salts to provide a process that is stable, fast acting, environmentally acceptable, has high capacity, and can be performed at room temperature. A preferred etchant composition is 100 gm/liter sodium persulfate, 3 volume % phosphoric acid and 0.058 molar sodium phosphate dibasic.

Docket No.  
EN997064

# Declaration and Power of Attorney For Patent Application

## English Language Declaration

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name,

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

COPPER CLEANING COMPOSITIONS, PROCESSES AND PRODUCTS DERIVED THEREFROM

the specification of which

(check one)

☒ is attached hereto.

☐ was filed on \_\_\_\_\_ as United States Application No. or PCT International Application Number \_\_\_\_\_ and was amended on \_\_\_\_\_ (if applicable)

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, Code of Federal Regulations, Section 1.56.

I hereby claim foreign priority benefits under Title 35, United States Code, Section 119(a)-(d) or Section 365(b) of any foreign application(s) for patent or inventor's certificate, or Section 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate or PCT International application having a filing date before that of the application on which priority is claimed.

Prior Foreign Application(s)			Priority Not Claimed
_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/>
_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/>
_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/>

I hereby claim the benefit under 35 U.S.C. Section 119(e) of any United States provisional application(s) listed below:

\_\_\_\_\_  
(Application Serial No.)

\_\_\_\_\_  
(Filing Date)

\_\_\_\_\_  
(Application Serial No.)

\_\_\_\_\_  
(Filing Date)

\_\_\_\_\_  
(Application Serial No.)

\_\_\_\_\_  
(Filing Date)

I hereby claim the benefit under 35 U. S. C. Section 120 of any United States application(s), or Section 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. Section 112, I acknowledge the duty to disclose to the United States Patent and Trademark Office all information known to me to be material to patentability as defined in Title 37, C. F. R., Section 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application:

\_\_\_\_\_  
(Application Serial No.)

\_\_\_\_\_  
(Filing Date)

\_\_\_\_\_  
(Status)  
(patented, pending, abandoned)

\_\_\_\_\_  
(Application Serial No.)

\_\_\_\_\_  
(Filing Date)

\_\_\_\_\_  
(Status)  
(patented, pending, abandoned)

\_\_\_\_\_  
(Application Serial No.)

\_\_\_\_\_  
(Filing Date)

\_\_\_\_\_  
(Status)  
(patented, pending, abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. *(list name and registration number)*

David L. Adour/Reg.#29,604  
 Lawrence R. Fraley/Reg.#26,885  
 Arthur J. Samodovitz/Reg.#31,297  
 John R. Pivnichny/Reg.#43,001  
 William H. Steinberg/Reg.#28,540  
 Robert S. Salzman/Reg.#25,607  
 Mark Levy/Reg.#29,188  
 David L. Banner/Reg.#39,898  
 Christopher A. Hughes/Reg.#26,914  
 Edward A. Pennington/Reg. #32,588  
 John E. Hoel/Reg.#26,279  
 Joseph C. Redmond, Jr./Reg.#18,753

Send Correspondence to: Mark Levy, Esq.  
 SALZMAN & LEVY  
 19 Chenango St., Ste. 606  
 Binghamton, NY 13901

Direct Telephone Calls to: *(name and telephone number)*  
 Mark Levy (607) 722-6600/Fax: (607) 724-2207

Full name of sole or first inventor	
Kathleen L. Covert (Deceased) by Kelly Hawley Executrix	
Sole or first inventor's signature	Date
Residence	
23 South Morningside Drive, Binghamton, NY 13905	
Citizenship	
US	
Post Office Address	
Same	

Full name of second inventor, if any	
John M. Lauffer	
Second inventor's signature	Date
Residence	
213 Lincoln Street Extension, Waverly, New York 14892	
Citizenship	
US	
Post Office Address	
Same	

Full name of third inventor, if any Peter A. Moschak	
Third inventor's signature	Date
Residence 317 Pixley Road, Chenango Forks, New York 13746	
Citizenship US	
Post Office Address Same	

Full name of fourth inventor, if any	
Fourth inventor's signature	Date
Residence	
Citizenship	
Post Office Address	

Full name of fifth inventor, if any	
Fifth inventor's signature	Date
Residence	
Citizenship	
Post Office Address	

Full name of sixth inventor, if any	
Sixth inventor's signature	Date
Residence	
Citizenship	
Post Office Address	